



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : A61K 6/083, C04B 28/28	A1	(11) International Publication Number: WO 92/21314 (43) International Publication Date: 10 December 1992 (10.12.92)
(21) International Application Number: PCT/US92/04164 (22) International Filing Date: 19 May 1992 (19.05.92) (30) Priority data: 708,988 31 May 1991 (31.05.91) US (71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, Post Office Box 33427, Saint-Paul, MN 55133-3427 (US). (72) Inventors: MITRA, Sumita, B. ; MITRA, Smarajit ; Post Office Box 33427, Saint-Paul, MN 55133 (US). (74) Agents: BJORKMAN, Dale, A. et al.; Minnesota Mining and Manufacturing Company, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).		(81) Designated States: AT (European patent), AU, BE (European patent), BR, CA, CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), GR (European patent), IT (European patent), JP, KR, LU (European patent), MC (European patent), NL (European patent), NO, PL, SE (European patent). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: UNIVERSAL WATER-BASED MEDICAL AND DENTAL CEMENT (57) Abstract Dental cement containing water, acid-reactive filler, water-miscible acidic polymer, an ethylenically-unsaturated moiety, photoinitiator, water-soluble reducing agent and water-soluble oxidizing agent. The cement has three curing modes, namely an acid-filler ionic reaction, a photoinitiated crosslinking reaction and a redox-initiated crosslinking reaction. The cement cures well in thick layers, and can be used without a dental curing light or with a light that is weak or defective.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FI	Finland	MI	Mali
AU	Australia	FR	France	MN	Mongolia
BB	Barbados	GA	Gabon	MR	Mauritania
BE	Belgium	GB	United Kingdom	MW	Malawi
BF	Burkina Faso	GN	Guinea	NL	Netherlands
BG	Bulgaria	GR	Greece	NO	Norway
BJ	Benin	HU	Hungary	PL	Poland
BR	Brazil	IE	Ireland	RO	Romania
CA	Canada	IT	Italy	RU	Russian Federation
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark	MG	Madagascar		
ES	Spain				

UNIVERSAL WATER-BASED MEDICAL AND DENTAL CEMENT

5 **Technical Field**

This invention relates to water-based medical and dental cements.

Background Art

10 Resin-based composite and restorative
materials generally have very high cohesive strength,
and accordingly are widely used in dentistry. However,
in recent years there has been a resurgence in
water-based cements. These water-based cements may
15 contain resinous components, but are distinguished by
containing substantial amounts of water. Examples
include metal oxide cements such as those described in
U.S. Pat. No. 3,655,605 and fluoroaluminosilicate glass
cements (also known as "glass ionomer cements") such as
20 those described in Example 6 of the '605 patent and in
U.S. Pat. Nos. 3,814,717, 4,043,327, 4,143,018, and
4,209,434. These water-based cements have also found
utility in medical applications such as the fabrication
of orthopedic bandages, as described in U. S. Pat. Nos.
25 4,043,327 and 4,243,567.

Typically, these cements are cured or hardened by combining a polyfunctional acid, water and an acid-reactive metal oxide or glass filler. Hardening occurs due to the reaction between the acidic groups of the polyfunctional acid and cations leached from the filler. More recently, light-curable water-based cements have appeared. Examples are shown in U.S. Pat. No. 4,872,936, European Pat. Application Nos. 0 323 120 and 0 329 268 and Australian Published Pat. Specification No. 46717/89. These light-curable cements include one or more ethylenically-unsaturated components and a suitable photoinitiator. Hardening

-2-

takes place independently from the acid-filler reaction mentioned above via crosslinking of the ethylenically-unsaturated component upon exposure of the photoinitiator to light or other activating energy.

5 A light-curable and apparently anhydrous cement is shown in European Pat. Application No. 0 391 619. It contains a number of ingredients, including benzoyl peroxide.

10 Although light-curable cements have many advantages, they do require use of a light. If the light is defective (for example, due to breakage or discoloration of the filters typically installed in the light path or through deterioration of the curing lamp), then the composition may undergo incomplete
15 light-curing polymerization. Also, owing to the need to insure adequate penetration of the light energy into the cement, thick restorations typically must be built up in separately cured thin layers. In some dental applications it may be impractical to use a curing
20 light. For example, when luting a metallic crown to a prepared tooth stump, light typically will not penetrate underneath the crown. Likewise, for endodontic applications, light may not penetrate the full depth of the endodontic preparation. On the other
25 hand a cement that cures only by dark reactions takes a long time to cure. During this time the cement may be prone to moisture contamination.

 Accordingly, presently available cements have not had universal applicability. This has led to the
30 appearance of many special-purpose products in the marketplace, with attendant need for the practitioner to maintain separate inventories of each cement, to undergo training in the use of more than one cement, and to avoid improper use through inadvertent selection
35 of the wrong cement.

-3-

Summary of the Invention

The present invention provides a cement having three curing modes. The cement cures through a first mechanism, via an acid-filler ionic reaction.

5 The cement cures through a second mechanism, via photoinitiated free radical crosslinking of an ethylenically-unsaturated component. Finally, the cement cures through a third mechanism, via redox-initiated free radical crosslinking of the

10 ethylenically-unsaturated component. The cement can be used in a wide variety of applications, and will provide good results even if a dental curing light is not used or is improperly used. The cement is water-based, and thus can be used under moist

15 conditions such as are typically present in the mouth.

The invention provides, in one aspect, a water-containing, ionically-hardenable, photocurable, ethylenically-unsaturated dental cement, comprising

- a) finely-divided acid-reactive filler,
- 20 b) water-miscible acidic polymer,
- c) photoinitiator,
- d) water-soluble reducing agent, and
- e) water-soluble oxidizing agent.

Preferably, the reducing agent and the oxidizing agent

25 are capable of initiating gelation of a 10:10:1 (weight basis) water:acrylamide:methylene bis-acrylamide mixture.

In a further aspect, the invention provides preferred cements in which the reducing agent or the

30 oxidizing agent are contained in microcapsules. The microcapsules improve shelf life and facilitate packaging.

Detailed Description

35 Generally, the cements of the invention are formulated in two parts, although formulations employing three or more parts can be made up if

desired. In a two part formulation, the first part typically is a powder portion containing the acid-reactive filler. The second part typically is a liquid portion containing the acidic polymer, water and one (but usually not both) of the water-soluble reducing agent and water-soluble oxidizing agent. If the reducing agent is present in the liquid portion, then the oxidizing agent is typically present in the powder portion, and vice-versa. The reducing agent and oxidizing agent can be combined in the powder portion or in the liquid portion through the use of a microencapsulation technique described in more detail below.

The invention is not limited to powder:liquid formulations. For example, one part anhydrous formulations containing filler, polymer, photoinitiator, reducing agent and oxidizing agent can be prepared. These can be sold in dry form and prepared for use by adding water. Also, two part paste:paste formulations can be prepared by adding to the acid-reactive filler a suitable polymerizable liquid that does not react with that filler (e.g., 2-hydroxyethyl methacrylate, or "HEMA"), yielding a first paste. The acidic polymer described above is combined with a suitable filler that does not react with the acidic polymer (e.g., ground quartz), yielding a second paste. The two pastes are prepared for use by stirring them together. Other useful configurations will be familiar to those skilled in the art. However, for simplicity, the remainder of this patent specification will refer to powder:liquid formulations unless specifically noted otherwise.

The cements of the invention contain water. The water can be present in the product as sold, or added by the dentist just prior to use. The water can be distilled, deionized or plain tap water. Generally, deionized water is preferred. The amount of water

-5-

should be sufficient to provide adequate handling and mixing properties and to permit the transport of ions in the filler-acid reaction. Preferably, water represents at least about 1%, mor preferably about 3%
5 to about 25%, and most preferably about 5% to about 20% of the total weight of ingredients used to form the cement.

The cements of the invention are ionically hardenable. By this is meant that they contain
10 ingredients that, when combined, can react via an ionic reaction to produce a hardened mass. The ionic reaction occurs between acid groups on the polymer and acid-reactive groups on the filler.

The cements of the invention are also
15 ethylenically-unsaturated. In other words, they contain at least one ethylenically-unsaturated moiety. The ethylenically-unsaturated moiety can be present as a separate ingredient (for example, as an acrylate- or methacrylate-functional monomer) or it can, if desired,
20 be present as a group on another ingredient such as the acidic polymer. A wide variety of ethylenically-unsaturated moieties can be used. A useful list of suitable materials is shown at page 9, line 13 through page 13, last line of Australian Published Pat.
25 Specification No. 46717/89. Of the many materials mentioned, water-miscible or water-soluble acrylates and methacrylates such as 2-hydroxyethyl methacrylate, hydroxymethyl methacrylate, 2-hydroxypropyl methacrylate, tetrahydrofurfuryl methacrylate, glycerol
30 mono- or di-methacrylate, trimethylol propane trimethacrylate, ethylene glycol dimethacrylate, polyethylene glycol dimethacrylate, urethane methacrylates, acrylamide, methacrylamide, methylene bis-acrylamide or methacrylamide, and diacetone
35 acrylamide and methacrylamide are preferred. Mixtures of ethylenically-unsaturated moieties can be used if desired. Preferably, the ethylenically-unsaturated

-6-

moieties are present as groups on the acidic polymer, as described in more detail below.

The cements of the invention also contain an acid-reactive filler. The filler should be
5 sufficiently finely-divided so that it can be conveniently mixed with the other ingredients and used in the mouth. Preferred average particle diameters for the filler are about 0.2 to about 15 micrometers, more preferably about 1 to 10 micrometers, as measured
10 using, for example, a sedimentation analyzer.

Suitable acid-reactive fillers include metal oxides, metal salts and glasses. Preferred metal oxides include barium oxide, calcium oxide, magnesium oxide and zinc oxide. Preferred metal salts include
15 salts of multivalent cations, for example aluminum acetate, aluminum chloride, calcium chloride, magnesium chloride, zinc chloride, aluminum nitrate, barium nitrate, calcium nitrate, magnesium nitrate, strontium nitrate and calcium fluoroborate. Preferred glasses
20 include borate glasses, phosphate glasses and fluoroaluminosilicate glasses. Fluoroaluminosilicate glasses are particularly preferred. Suitable fillers are also available from a variety of commercial sources familiar to those skilled in the art. For example,
25 suitable fillers can be obtained from a number of commercially available glass ionomer cements, such as "GC Fuji LC" cement and "Kerr XR" ionomer cement. Mixtures of fillers can be used if desired.

If desired, the filler can be subjected to a
30 surface treatment. Suitable surface treatments include acid washing, treatment with phosphates, treatment with chelating agents such as tartaric acid, treatment with a silane as described in Australian Published Pat. No. 46717/89, and treatment with an acidic silanol
35 solution.

The amount of filler should be sufficient to provide a cement having desirable mixing and handling

-7-

properties before cure, and good cement performance after cure. Preferably, the filler represents less than about 90%, mor preferably about 25% to about 85%, and most preferably about 50% to about 75% by weight of
5 the total weight (including water) of the unset cement components.

The acidic polymer need not be entirely water soluble, but it should be at least sufficiently water-miscible so that it does not undergo substantial
10 sedimentation when combined with the liquid ingredients of the cement. Suitable acidic polymers include those listed at column 2, line 62 through column 3, line 6 of U.S. Patent No. 4,209,434. Preferred acidic polymers include homopolymers and copolymers of alkenoic acids
15 such as acrylic acid, itaconic acid and maleic acid. Suitable polymers are also available from a wide variety of commercial sources, and many are found in currently-available glass ionomer cements. As will be appreciated by those skilled in the art, the polymer
20 should have a molecular weight sufficient to provide good storage, handling and mixing properties. A preferred molecular weight is about 5000 to about 100,000 weight average molecular weight (M_w), evaluated against a polystyrene standard using gel permeation
25 chromatography. Preferably, the acidic polymer contains one or more ethylenically-unsaturated groups. Suitable ethylenically-unsaturated acidic polymers are described in U.S. Pat. No. 4,872,936 and in European Pat. Application No. 0 323 120. Preferably, the
30 numbers of acid groups and ethylenically-unsaturated groups are adjusted to provide an appropriate balance of properties in the cement, both during the setting reaction and after the cement has hardened. Acidic polymers in which about 10 to about 30% of the acidic
35 groups have been replaced with ethylenically-unsaturated groups are preferred.

The amount of acidic polymer in the cement should also be sufficient to provide a desired balance of physical properties. A preferred acidic polymer amount is at least about 5%, more preferably about 10 to about 50%, and most preferably about 10 to about 30% of the total weight (including water) of the unset cement components.

The photoinitiator should be capable of promoting free radical crosslinking of the ethylenically-unsaturated component on exposure to light of a suitable wavelength and intensity. It also preferably is sufficiently shelf-stable and free of undesirable coloration to permit its storage and use under typical dental conditions. Visible light photoinitiators are preferred. The photoinitiator preferably is water-soluble or water-miscible.

Photoinitiators bearing polar groups usually have a sufficient degree of water-solubility or water-miscibility. The photoinitiator frequently can be used alone but typically it is used in combination with a suitable donor compound or a suitable accelerator (for example, amines, peroxides, phosphorus compounds, ketones and alpha-diketone compounds).

Preferred visible light-induced initiators include camphorquinone (which typically is combined with a suitable hydrogen donor such as an amine), diaryliodonium simple or metal complex salts, chromophore-substituted halomethyl-s-triazines and halomethyl oxadiazoles. Particularly preferred visible light-induced photoinitiators include combinations of an alpha-diketone, e.g., camphorquinone, and a diaryliodonium salt, e.g., diphenyliodonium chloride, bromide, iodide or hexafluorophosphate, with or without additional hydrogen donors (such as sodium benzene sulfinate, amines and amine alcohols). Preferred ultraviolet light-induced polymerization initiators include ketones such as benzyl and benzoin,

-9-

and acyloins and acyloin ethers. Preferred commercially available ultraviolet light-induced polymerization initiators include 2,2-dimethoxy-2-phenylacetophenone ("IRGACURE 651") and benzoin methyl ether (2-methoxy-2-phenylacetophenone), both from Ciba-Geigy Corp.

The photoinitiator should be present in an amount sufficient to provide the desired rate of photopolymerization. This amount will be dependent in part on the light source, the thickness of the cement layer to be exposed to radiant energy, and the extinction coefficient of the photoinitiator. Typically, the photoinitiator components will be present at a total weight of about 0.01 to about 5%, more preferably from about 0.1 to about 5%, based on the total weight (including water) of the unset cement components. The photoinitiator can be included in either the paste or liquid parts of the cement.

The water-soluble reducing agent and water-soluble oxidizing agent are most conveniently discussed together. They should react with or otherwise cooperate with one another to produce free-radicals capable of initiating polymerization of the ethylenically-unsaturated moiety. The reducing agent and oxidizing agent preferably are sufficiently shelf-stable and free of undesirable colorization to permit their storage and use under typical dental conditions. They should be sufficiently water-soluble to permit ready dissolution in (and discourage separation from) the other components of the cement. The reducing agent and oxidizing agent should also be sufficiently soluble and present in an amount sufficient to permit an adequate free-radical reaction rate. This can be evaluated by combining all of the ingredients of the cement except for the filler under safelight conditions, and observing whether or not a hardened mass is obtained.

-10-

The reducing agent and oxidizing agent preferably are sufficiently water-soluble and have sufficient reduction and oxidation potentials to initiate gelation of an aqueous crosslinkable acrylamide solution. This can be evaluated by adding 2 weight % each of the reducing agent and the oxidizing agent to an aqueous acrylamide:methylene bis-acrylamide solution (described below in Table Ia) and observing whether or not gelation occurs within 30 minutes.

Useful reducing agent/oxidizing agent pairs are shown in "Redox Polymerization", G. S. Misra and U. D. N. Bajpai, Prog. Polym. Sci., 8, 61-131 (1982).

Preferred reducing agents include ascorbic acid, cobalt (II) chloride, ferrous chloride, ferrous sulfate, hydrazine, hydroxylamine (depending upon the choice of oxidizing agent) oxalic acid, thiourea, and salts of a dithionite or sulfite anion. Preferred oxidizing agents include cobalt (III) chloride, tert-butyl hydroperoxide, ferric chloride, hydroxylamine (depending upon the choice of reducing agent), perboric acid and its salts, and salts of permanganate or persulfate anion. Hydrogen peroxide can also be used, although it has been found to interfere with the photoinitiator in some instances.

The amount of reducing agent and oxidizing agent should be sufficient to provide the desired degree of polymerization of the ethylenically-unsaturated component. The preferred amount for each of the reducing agent and oxidizing agent is about 0.01 to about 10%, more preferably about 0.02 to about 5%, based on the total weight (including water) of the unset cement components.

As mentioned above, the reducing agent or the oxidizing agent can be microencapsulated. This will generally enhance shelf stability and permit packaging both the reducing agent and oxidizing agent together. For example, through appropriate selection of the

-11-

encapsulant, both the oxidizing agent and reducing agent can be combined with the filler and kept in a storage-stable state. Likewise, through appropriate selection of a water-insoluble encapsulant, the
5 reducing agent and oxidizing agent can be combined with water and the acidic polymer and maintained in a storage-stable state.

Either water-soluble or water-insoluble encapsulants can be employed. However, water-insoluble
10 encapsulants are preferred, as they generally provide better long term storage stability under moist or humid conditions. Although the use of a water-insoluble encapsulant may initially seem inappropriate in a water-based cement, it has been found that vigorous
15 mechanical mixing generally will be sufficient to break apart the capsule walls and permit adequate release of the encapsulated reducing agent or oxidizing agent and subsequent cure of the cement.

Preferably the encapsulant is a medically
20 acceptable polymer and a good film former. Also, the glass transition temperature (T_g) of the encapsulant preferably is above room temperature.

A wide variety of encapsulants can be used, with cellulosic materials as cellulose acetate,
25 cellulose acetate butyrate, ethyl cellulose, hydroxymethyl cellulose and hydroxyethyl cellulose being preferred. Other encapsulants include polystyrene, copolymers of polystyrene with other vinylic monomers, polymethylmethacrylate, copolymers of
30 methylmethacrylate with other ethylenically-unsaturated monomers, and other materials that will be familiar to those skilled in the art of encapsulation.

The capsules themselves need not be perfectly spherical nor uniformly shaped. It is merely
35 sufficient that they entrain or entrap the encapsulated reducing agent or oxidizing agent in a manner sufficient to permit storage of the encapsulated

-12-

material in a cement component without leading to undesirable premature polymerization.

To encapsulate the reducing agent or oxidizing agent in a water-insoluble encapsulant, it is preferred to dissolve the encapsulant in a suitable water-immiscible solvent such as methyl acetate, ethyl acetate or methylene chloride. Meanwhile, the reducing agent or oxidizing agent is dissolved in water. The water solution can then be added to the solution of encapsulant and water-immiscible solvent. Stirring or other high speed shear techniques preferably are used to promote uniform microcapsule formation. The capsule shells are formed around the aqueous solution droplets either by evaporation of the water-immiscible solvent or by the addition of a second water-immiscible solvent (e.g., n-hexane) that will precipitate the encapsulant. The capsules can then be removed by cooling and filtration.

To encapsulate the reducing agent or oxidizing agent in a water-soluble encapsulant, the dry reducing agent or oxidizing agent is preferably suspended in a stirred solution of the encapsulant in a water-immiscible organic solvent. Vigorous stirring will promote uniform encapsulation of the reducing agent or oxidizing agent. The capsules can be formed by evaporation or by precipitation and then removed using the techniques described above.

If desired, the cements of the invention can contain adjuvants such as pigments, nonvitreous fillers, inhibitors, accelerators, viscosity modifiers, surfactants, and other ingredients that will be apparent to those skilled in the art.

The cements of the invention can be mixed and clinically applied using conventional techniques. However, the cements will have particular utility in clinical applications where cure of a conventional light-curable cement may be difficult to achieve. Such

-13-

applications include deep restorations, large crown build-ups, endodontic restorations, luting of metallic crowns or other light-impermeable prosthetic devices to teeth, and other restorative applications in

5 inaccessible areas of the mouth. The three-way cure mechanism facilitates thorough, uniform cure and retention of good clinical properties. The cements of the invention thus show good promise as a universal restorative.

10 The cements of the invention are further described in the following illustrative examples, which should not be construed as limiting the scope of the invention. Unless otherwise indicated, all parts and percentages are on a weight basis.

15

EXAMPLE 1**Cements Prepared Using Various Curing Modes**

A test solution was prepared by combining the ingredients set out below in Table Ia:

20

Table Ia

Ingredients	Parts
Acrylamide	30
Methylene bis-acrylamide	3
Water	30

25

In a series of four runs a 2g portion of the test solution was placed in a glass test tube. For each
30 run, 2% of the ingredients set out below in Table Ib were added to a separate test tube with shaking:

-14-

Table Ib

Run N .	Add d Ingr dients
1	Potassium Persulfate Ascorbic Acid
2	Potassium Persulfate Thiourea
3	Potassium Persulfate Oxalic Acid
4	Ammonium Persulfate Ascorbic Acid

10 The contents of the two test tubes were combined with shaking. For each run, gelation and an exotherm were observed within seven minutes.

The ingredients set out below in Table IIa were mixed, melted in an arc furnace at about
 15 1350-1450°C, poured from the furnace in a thin stream and quenched using chilled rollers to provide an amorphous single-phase fluoroaluminosilicate glass:

Table IIa

Ingredient	Parts
SiO ₂	37
AlF ₃	23
SrO	20
Al ₂ O ₃	10
AlPO ₄	7
Na ₂ AlF ₆	6
P ₂ O ₅	4

20
 25
 30 The glass was ball-milled to provide a pulverized frit with a surface area of 2.6 m²/g measured using the Brunauer, Emmet and Teller (BET) method. The pulverized glass was labeled "Control Glass". 20 Parts

-15-

of the Control Glass were mixed with a solution of 0.1 parts ascorbic acid (a water-soluble reducing agent) in 39.5 parts methanol, and stirred for 10 minutes using a magnetic stirrer. The wet glass was poured into a dish to a depth less than 1 cm, and then dried in a 45°C oven for 16 hours. The dried glass was sieved through a 74 μ m mesh screen, and labeled "Glass A".

The ingredients set out below in Table IIb were mixed using a paint shaker to provide two cement-forming liquids labeled "Control Liquid" and "Liquid A". Each liquid contained ethylenically-unsaturated components (as groups on the copolymer and as a separate ingredient), and carboxylic acid (as groups on the copolymer). Liquid A also contained potassium persulfate (a water-soluble oxidizing agent):

Table IIb

Ingredient	Cement-forming liquids, parts	
	Control Liquid	Liquid A
Copolymer ¹	50	50
Water ²	30	30
HEMA ³	20	20
(C ₆ H ₅) ₂ I ⁺ PF ₆ ⁻	0.7	0.7
CPQ ⁴	0.25	0.25
BHT ⁵	0.1	0.1
K ₂ S ₂ O ₈	---	0.05

¹ Ethylenically-unsaturated acidic copolymer prepared like the precipitated dry polymer of EXAMPLE 11 of European Published Pat. Application No. 0 323 120.

² Distilled water.

³ 2-Hydroxyethyl methacrylate.

⁴ Camphorquinone.

⁵ Butylated hydroxytoluene.

-16-

The absorbic acid-treated Glass A and the potassium persulfate-containing Liquid A were hand-spatulated at a 1.4:1 powder:liquid ratio. The resulting cement exhibited good mixing properties and a two minute working time. The end of the working period coincided with a loss of gloss and a marked decrease in tack.

In a series of 4 runs, the glasses Control Glass and Glass A, and the liquids Control Liquid and Liquid A, were hand-spatulated for one minute at a 1.4:1 powder:liquid ratio, then packed into a 4 mm inside diameter glass tube, capped with silicone rubber plugs, and axially compressed at about 0.28 MPa. About 1.5 minutes after the start of mixing, samples for the cements of Runs nos. 1 and 3 were exposed for 80 seconds to light from two oppositely-disposed visible light curing lamps ("VISILUX 2" curing lamp, 3M) and then the axial pressure was removed. The cements of Run nos. 2 and 4 were allowed to remain under pressure for 10 minutes and were not photopolymerized.

Each of the cements of Run nos. 1-4 was allowed to stand for one hour at ambient pressure, 50% relative humidity and 37°C. The samples were cut on a diamond saw to form cylindrical plugs 2 mm long for measurement of Diametral tensile strength ("DTS"), and 8 mm long for measurement of compressive strength ("CS"). The plugs were stored in distilled water at approximately 37°C for about 24 hours. DTS and CS values were determined for 5 samples of each cement according to ISO specification 7489.

The results are set out below in Table III, along with a brief identification of the applicable cure mechanism for each sample.

Table III

Run No.	Glass	Liquid	Photo Curing	Cure Mech-anism	CS	DTS
1	Glass A	Liquid A	Yes	IPR ¹	154	27
2	Glass A	Liquid A	No	IR ²	141	20
3	Control Glass	Control Liquid	Yes	IP ³	155	26
4	Control Glass	Control Liquid	No	I ⁴	37	3

1 "IPR" = Acid-base ionomer reaction ("I") plus
 10 photoinitiated reaction ("P") plus redox
 reaction ("R").

2 "IR" = I reaction plus R reaction.

3 "IP" = I reaction plus P reaction.

4 "I" = I reaction.

15

The results in Table III illustrate the improvement provided by the invention. When a cement of the invention was cured using all three cure mechanisms (Run no. 1), CS and DTS were experimentally equivalent
 20 to the values obtained for a light-curable ionomer cement cured in thin section using two cure mechanisms (Run no. 3). When the photoinitiated "P" mechanism was omitted but the redox "R" reaction was present (Run no. 2), CS and DTS were maintained at respectably high
 25 levels. This would correspond to curing a cement of the invention in a very thick section, or to curing it without a properly-operating curing lamp. With or without photocuring, the cement of the invention had substantially better CS and DTS than a cement cured
 30 using only the ionomer "I" reaction (Run no. 4). Thus a cement of the invention could be cured without a curing lamp, or with a defective curing lamp, and still provide a strong cured cement.

-18-

In a further comparison, the Control Liquid was combined with 0.05% benzoyl peroxide and shaken on a paint mixer for two days. The peroxide did not dissolve, demonstrating that a water-soluble oxidizing agent was required even though the Control Liquid contained a substantial portion of nonaqueous resin.

EXAMPLE 2

Comparison of Dentin Adhesion

Using Various Curing Modes

Five bovine teeth of similar age and appearance were partially embedded in circular acrylic disks so that the enamel was exposed. The exposed portion of each tooth was ground flat and parallel to the acrylic disc using Grade 120 silicon carbide paper-backed abrasive mounted on a lapidary wheel, until the dentin was exposed. Further grinding and polishing of the teeth was carried out by mounting Grade 320 silicon carbide paperbacked abrasive on the lapidary wheel. During the grinding and polishing steps, the teeth were continuously rinsed with water. The polished teeth were stored in distilled water and used for testing within 2 hours after polishing. The polished teeth were removed from the water and dried using a stream of compressed air.

A mold made from a 2.5 mm thick "TEFLON" polytetrafluoroethylene sheet with a 5 mm diameter circular hole through the sheet was clamped to each polished tooth so that the central axis of the hole in the mold was normal to the polished tooth surface. The mold was fitted with a sleeve made from a no. 4 gelatin capsule. The sleeve was filled with a hand-spatulated glass ionomer cement mixture. The cement was light-cured for 60 seconds, allowed to stand for about 5 minutes at room temperature, then stored in distilled water at 37°C for 24 hours. Dark-cured samples were

-19-

not photocured, but were allowed to stand at room temperature under a yellow safelight for 15 minutes before placing them in water. The molds were then carefully removed, leaving a molded cement button attached to each tooth.

Adhesive strength was evaluated by mounting the acrylic disk in a holder clamped in the jaws of an "INSTRON" tensile testing apparatus with the polished tooth surface oriented parallel to the direction of pull. A loop of 0.44 mm diameter orthodontic wire was placed around the base of the cement button adjacent to the polished tooth surface. The ends of the orthodontic wire were clamped in the pulling jaw of the tensile testing apparatus, placing the bond in shear stress. The bond was stressed until it (or the cement button) failed, using a crosshead speed of 2 mm/min and an average of 5 or more samples.

A freshly-mixed sample made from a 1.4:1 mixture of Glass A and Liquid A was evaluated for adhesion to dentin using the procedure described above. With photocuring, the average measured adhesive shear bond strength for 6 samples was 8.9 MPa. If photocuring was omitted, the average measured shear bond strength dropped to 2.9 MPa. A control cement prepared from the Control Glass and the Control Liquid had an average measured adhesive shear bond strength of 4.6 MPa. If photocuring was omitted, the average measured adhesive shear bond strength dropped to less than 1 MPa. Accordingly, use of a cement with all three cure modes yielded the highest average dentin adhesion.

Dark (non-photopolymerized) set time was evaluated using a modified version of ISO standard 7489. The measurement was performed under a yellow safelight at 21-23°C, and resistance to indentation by a 400 g Gilmore needle was evaluated 60 seconds after the start of mixing and every 10 seconds thereafter.

-20-

The cement of the invention had a set time of 11.5 minutes, and the control cement had a set time greater than 36 minutes.

5

EXAMPLE 3**Preparation of Powders Containing
Oxidizing and Reducing Agents**

A sample of the untreated Control Glass was slurry-treated with 0.1% potassium persulfate using the method of EXAMPLE 1. The treated glass was labeled "Glass B". A further sample of the Control Glass was slurry-treated with 0.5% ascorbic acid. The treated glass was labeled "Glass C". Equal portions of Glass B and Glass C were hand-mixed to provide a dry glass containing both an oxidizing agent and a reducing agent. This glass was labeled "Glass D".

When Glass D and the Control Liquid were combined in a 1.4:1 powder:liquid ratio and evaluated using the method of EXAMPLE 1, a cement with a CS of 152 MPa and a DTS of 28 MPa was obtained. The cement had an average measured adhesive shear bond strength of 7.8 MPa.

EXAMPLE 4**25 Cements Prepared from Liquids Containing Oxidizing
Agent and Powders Containing Reducing Agent**

Several liquid solutions were prepared from the ingredients set out below in Table IVa:

Tabl IVa

Ingredient	Parts
Copolymer of EXAMPLE 1	50
Water	30
HEMA	20
$(C_6H_5)_2I^+PF_6^-$	0.7
CPQ	0.25
BHT	0.10
$K_2S_2O_8$	See Table IVb

Several portions of a glass like the Control Glass of EXAMPLE I (but with a surface area of 3.3 m²/g) were slurry-treated with various methanolic ascorbic acid solutions. The theoretical amounts of ascorbic acid on the treated glass are set out below in Table IVb.

Cements were formed by combining the treated glasses and liquids at a 1.4:1 powder:liquid ratio. Dark set times were tested according to ISO standard DIS 9917, using a 400 g indenter. Approximately 30 seconds were required to mix the cement, transfer it to the mold specified in the ISO standard, and place the mold in a 37°C oven (also specified in the ISO standard). By then, some of the faster cements had already begun to set. These set times are indicated as "≤30" in Table IVb.

-22-

Tabl IVb

ISO SET Time, s c (dark)							
% $K_2S_2O_8$ in Liquid	% Asc rbic Acid on Glass						
	0.05	0.10	0.25	0.5	1.0	1.5	2.0
0.025	600	400	360	280	240	120	100
0.05	330	280	230	120	80	70	80
0.10	--	160	70	50	50	40	40
0.25	--	100	50	40	40	≤30	≤30
0.5	--	--	--	40	35	35	35
1.0	--	--	--	35	≤30	35	35
1.5	--	--	--	≤30	≤30	≤30	≤30
2.0	--	--	--	35	≤30	≤30	≤30

The above data shows dark set times for cements containing varying amounts of reducing agent and oxidizing agent. The range of observed set times

performed at an elevated temperature (37°C), room temperature set times likely would be longer.

EXAMPLE 5

Cements Prepared from Liquids Containing
Oxidizing Agent and Inhibitor

The following liquid solutions were prepared:

-23-

Table V

Ingredient	Parts			
	Control Liquid 2	Liquid B	Liquid C	Liquid D
5 Copolymer of EXAMPLE 1	100	100	100	100
Water	60	60	60	60
HEMA	40	40	40	40
CPQ	1.0	1.0	1.0	1.0
10 BHT	0.1	0.1	0.1	0.1
$K_2S_2O_8$	0.05	0.05	0.05	0.05
4-methoxyphenol	--	0.1	0.5	1.0

15 The untreated glass used in EXAMPLE 4 was slurry-treated by mixing together the ingredients set out below in Table VI. Each slurry was poured into a plastic-lined tray, dried overnight at 45°C, and then
 20 sieved through a 74 μ m mesh screen to make Glasses E, F and G.

Table VI

Ingredient	Parts		
	Glass E	Glass F	Glass G
25 methanol	40	40	40
glass powder	20	20	20
diphenyliodonium chloride	0.40	0.40	0.40
30 ascorbic acid	0.01	0.02	0.05

Dark set times were determined using the method of EXAMPLE 4. The results are set out below in Table VII.

35

-24-

Tabl VII

	Dark s t tim , s c nds		
	Glass E	Glass F	Glass G
Control Liquid 2	330	280	230
Liquid B	870	840	510
Liquid C	930	840	810
Liquid D	900	870	810

The above data shows that adding 4-methoxyphenol can increase set times, thus providing some measure of control over polymerization.

EXAMPLE 6

Cement Prepared Using Thiourea as Reducing Agent

20 Parts of the untreated glass of EXAMPLE 4 were slurried for 30 minutes in a solution of 0.15 parts thiourea in 40 parts methanol. The treated glass was dried overnight at 45°C and sieved through a 74 μ m mesh screen. A liquid solution was prepared from the ingredients set out below in Table VIII.

Table VIII

Ingredient	Parts
Copolymer of EXAMPLE 1	50
Water	30
HEMA	20
$(C_6H_5)_2I^+PF_6^-$	1.0
CPQ	0.25
BHT	0.10
$K_2S_2O_8$	0.05

Cement mixes were prepared at a 1.4:1 powder:liquid ratio, placed in the ISO 9917 mold described in EXAMPLE 4, and photocured from above for 60 seconds

-25-

using a VISILUX 2 dental curing light. "Barcol" hardness values were determined using a Barber-Colman hardness tester and indenter "GYZJ935". The measured hardness values were 51 on the top and 48 on the bottom of the molded cement sample, indicating that very uniform cure was obtained.

EXAMPLE 7**Cement Prepared from a Liquid Containing Polycarboxylic Acid Without Pendant Ethylenic Unsaturation**

A liquid solution containing a separate ethylenically-unsaturated ingredient was prepared by mixing together the ingredients set out below in Table IX:

Table IX

Ingredient	Parts
33% solution of polyacrylic acid ($M_w=25,000$) in water	6
HEMA	4
UDMA ¹	0.3
GDMA ²	0.3

¹ Trimethylhexamethylene diisocyanate end-capped at a 2:1 molar ratio with HEMA

² Glyceryl dimethacrylate

A mixture of 0.8 parts Glass B and 0.8 parts Glass C was hand-spatulated with 1 part of the liquid. Using the method of EXAMPLE 2, a dark set time of 10 minutes, 10 seconds was observed. The average of the top and bottom Barcol hardness values after 1 hour was 43.

A control cement was prepared by mixing 1.6 parts of the untreated Control Glass with 1 part of the liquid. A dark set time of 50 minutes was observed. The average of the top and bottom Barcol hardness values after 1 hour was only 9.

-26-

EXAMPLE 8

Mixtur of C mmercial Cement Liquid with
Powder Containing Oxidizing Ag nt and Reducing Ag nt

1 Part "GC Fuji LC" Liquid (the liquid
5 portion of a commercial light-curable glass ionomer
cement from GC Corp.) was hand-spatulated with 1.4
parts Glass D (which was made by combining 0.7 parts of
the potassium persulfate-treated Glass B and 0.7 parts
of the ascorbic acid-treated Glass C). Using the
10 method of EXAMPLE 7, a dark set time of 10 minutes and
an average Barcol harness after 2 hours of 72 were
observed.

A control cement was prepared by hand-
spatulating 1 part GC Fuji LC Liquid with the untreated
15 Control Glass and stored under a yellow safelight.
After 1 hour and 45 minutes, the mixture had not set.

This example demonstrates that a commercial
light-curable glass ionomer cement can readily be
modified to improve its dark set time.

20

Microencapsulation of $K_2S_2O_8$ in Cellulose
Acetate Butyrate (CAB)

8.0 Parts CAB containing 18% butyl groups
25 were dissolved in 800 parts methylene chloride.
Separately, 5.0 parts $K_2S_2O_8$ were dissolved in 100 parts
water. 330 Parts of the methylene chloride solution
were transferred to a stainless steel vessel suspended
in a room temperature water bath. A stirring impeller
30 was suspended in the vessel and spun at 700 rpm. To
the stirred solution was added 50 parts of the $K_2S_2O_8$
solution. The temperature of the water bath was raised
to 37-38°C, thereby slowly evaporating the methylene
chloride. After one-half hour, ice was added to the
35 water bath to lower the temperature to 24°C. 165 Parts
n-hexane were added slowly to the vessel in order to
precipitate the encapsulated oxidizing agent. The

-27-

precipitate was filtered, washed with cold n-hexane and dried under vacuum. The resulting dry microcapsules were deagglomerated in an electric coffee grinder, yielding a very light fluffy powder.

5

EXAMPLE 10**Powder Containing Microencapsulated Oxidizing Agent and Unencapsulated Reducing Agent**

67 Parts of the untreated glass used in
10 EXAMPLE 4 were mixed on a roll mill for 1 hour with 0.232 parts of the microcapsules of EXAMPLE 9. 20 Parts of the resulting treated glass were mixed on a roll mill for one-half hour with 20 parts of a fresh sample of Glass C. The resulting mixture was labelled
15 "Glass H". It was combined at a 1.4:1 powder:liquid ratio with Control Liquid 3 (a liquid like the Control Liquid of EXAMPLE 1, but containing 1 part rather than 0.7 parts $(C_6H_5)_2I^+PF_6^-$) and evaluated using the method of EXAMPLE 2. A set time of 12.5 minutes was observed.

20 Portions of Glass H were subjected to accelerated aging for 4 days and 8 days at 45°C. Set time measurements showed that the dark curing reaction was not slowed, thus indicating that the microcapsules had excellent storage stability.

25

EXAMPLE 11**Microencapsulation of Ascorbic Acid in CAB**

3 Parts ascorbic acid were dissolved in 60 parts water. 8 Parts CAB were dissolved in 800 parts
30 dichloromethane. 330 Parts of the CAB solution and 50 parts of the ascorbic acid solution were added to a stainless steel vessel and stirred at 708 rpm. A 38-40°C water bath was placed under the vessel. 165 Parts n-hexane were added slowly to the stirred mixture
35 over a one-half hour period. A granular precipitate formed. stirring was continued for 15 additional minutes. The warm water bath was replaced with an

-28-

ice-water bath, resulting in the formation of additional precipitate. The precipitate was filtered, washed with n-hexane and dried under vacuum. The dried product was ground to a fine powder.

5

EXAMPLE 12**Silanol-treated Glass Powder Containing
Microencapsulated $K_2S_2O_8$, and Ascorbic Acid**

4 Parts "A-174" gamma-methacryloxypropyl
10 trimethoxysilane (Union Carbide Corp.), 25 parts
methanol, and 25 parts water were mixed, then acidified
with trifluoroacetic acid until the pH reached 3.3.
The mixture was stirred for 15 minutes at room
temperature, yielding a silanol-containing treating
15 solution. 100 Parts of a glass like the Control Glass
of EXAMPLE 1 (but having a surface area of $2.8 \text{ M}^2/\text{g}$
rather than $2.6 \text{ M}^2/\text{g}$) were combined with the silanol
treating solution, slurried for 1.5 hours at room
temperature, dried overnight at 45°C , and sieved
20 through a 74 μm mesh screen. A portion of the treated
powder (5 parts) was mixed with 0.06 parts of
microencapsulated potassium persulfate of EXAMPLE 9.
Another portion of the treated powder (5 parts) was
mixed with 0.06 parts of the microencapsulated ascorbic
25 acid of EXAMPLE 11. The two powder portions were
combined and then roll-milled for one-half hour. The
resulting blended powder was combined at a 2.2:1
powder:liquid ratio with Control Liquid 4 (a liquid
like Control Liquid 3, but containing 0.05 parts BHT
30 rather than 0.1 parts). The resulting cured cement was
evaluated for CS and DTS using the method of EXAMPLE 1
(but with a 60 second photocure rather than 80
seconds). The respective CS and DTS values were 195
MPa and 38 MPa. If photocuring was omitted, the
35 respective CS and DTS values were 180 MPa and 25 MPa.

Adhesion to enamel was evaluated by generally
following the procedure of EXAMPLE 2. However, the

-29-

potted teeth were ground to expose only the enamel surface. The polished enamel surface was etched for 15 seconds using gelled 37% phosphoric acid, washed for 30 seconds with water and then dried using compressed air.

5 The measured adhesion to etched enamel was 18 MPa.

EXAMPLE 13

Microencapsulation by Precipitative Method

The three separate solutions whose
10 compositions are set out below in Table X were each placed in separate addition funnels:

Table X

Run No.	Solution
15 1	3 parts ascorbic acid in 60 parts water
2	3 parts $K_2S_2O_8$ in 60 parts water
3	3 parts $(NH_4)_2S_2O_8$ in 60 parts water

20 In a series of three separate runs, 50 parts of one of the solutions shown above were added to 366 parts of a stirred 1% solution of CAB in ethyl acetate contained in a stainless steel vessel immersed in a 4°C water
25 bath. The stirrer speed was maintained at 700 rpm and the bath temperature was maintained at 4°C. 267 Parts of ice cold n-hexane were added dropwise to the stirred solution over a 30 minute period. Granular spherical microcapsules were formed, as evidenced by microscopic
30 examination. Stirring was continued for an additional 15 minutes. The granular precipitate was filtered, washed with ice-cold n-hexane, dried under vacuum and then deagglomerated in an electric coffee mill.

35

-30-

EXAMPLE 14**Preparation of Tri-Cur Cement
from Silanol-Treated Glass Powder**

To 100 parts of a silanol-treated glass like
5 that of EXAMPLE 12 were added 0.55 parts of the
ascorbic acid microcapsules of Run no. 1 of EXAMPLE 13,
and 0.1 parts of the $K_2S_2O_8$ microcapsules of Run no. 2
of EXAMPLE 13. The mixture was mixed on a roll mill
for 1 hour. Using the method of EXAMPLE 4, the dark
10 set time was determined to be 4 minutes, 20 seconds.
Using the method of EXAMPLE 12, the respective CS and
DTS values after light-curing were determined to be 210
MPa and 31 MPa.

15

EXAMPLE 15**Preparation of Tri-Cure Cement from
Microencapsulated $(NH_4)_2S_2O_8$ and Ascorbic Acid**

A solution of 2 parts A174 silane, 12.5 parts
methanol, 12.5 parts water and 0.22 parts acetic acid
20 was stirred for 30 minutes, combined with 50 parts of
the untreated glass of EXAMPLE 12, and stored for 24
hours at room temperature, dried overnight at 45°C, and
sieved through a 74 μm mesh screen.

20 Parts of the resultant powder were added
25 to 0.11 parts of the microencapsulated ascorbic acid of
Run no. 1 of EXAMPLE 13 and 0.02 parts of the
microencapsulated ammonium persulfate of Run no. 3 of
EXAMPLE 13. The powders were mixed by roll-milling for
about 1 hour. When evaluated as in EXAMPLE 14, the
30 dark set time was determined to be 4 minutes, 20
seconds, and the CS and DTS values were determined to
be 208 MPa and 30 MPa.

EXAMPLE 15

35

Modification of Commercial Cements

In a first run, 4.5 parts "GC Fuji LC" light-
curable glass ionomer cement were combined with 0.025

-31-

parts of the ascorbic acid microcapsules of Run no. 1 of EXAMPLE 13 and 0.0045 parts of the potassium persulfate microcapsules of Run no. 2 of EXAMPLE 13. The resulting powder mixture was roll-milled for one half hour. The powder was labeled "Modified GC Glass".

As a second run, 4.1 parts "Kerr XR" ionomer powder (Kerr Division of Sybrón, Inc.) were combined with 0.0336 parts of the ascorbic acid microcapsules and 0.0044 parts of the potassium persulfate microcapsules. After roll-milling, the resulting powder was labelled "Modified Kerr Glass".

The modified glasses and the unmodified commercial glasses were independently combined at a 1.4:1 powder:liquid ratio with the corresponding commercial liquids supplied by the manufacturers, and permitted to harden without photocuring. The resulting cements were evaluated for room temperature and ISO dark set time using the methods of EXAMPLES 2 and 4. The cements were also evaluated for Barcol hardness using the method of EXAMPLE 6. Set out below in Tables XIa and XIb are the set time and Barcol hardness values for each cement.

Table XIa

	GC Cement	
	Unmodified	Modified
25	Dark Set Time	
	Room Temperature	35 min 12 min 30 sec
	ISO (37°C)	8 min 40 sec 5 min 20 sec
	Barcol Hardness	
	Room Temperature	
30	After 15 minutes	0 23
	After one hour	15 47
	ISO (37°C)	
	After 15 minutes	22 22
	After one hour	34 54

Tabl XIb

	K rr Cem nt	
	Unmodified	Modified
Dark Set Time		
5 Room Temperature	35 min	12 min 30 sec
ISO (37°C)	14 min	5 min 40 sec
Barcol Hardness		
Room Temperature		
After 15 minutes	0	0
10 After one hour	0	24
ISO (37°C)		
After 15 minutes	0	0
After one hour	8	34

15

As the above data illustrates, under dark conditions the modified cements set more rapidly and reached a higher ultimate hardness than the unmodified cements.

20 The modified cements would therefore be well suited to deep cure restorations, cure without a light or with a faulty light, and other low light situations.

Although this invention has been described using certain illustrative examples, it should be understood that the invention is not limited to the specific exemplary embodiments shown in this
25 specification.

-33-

CLAIMS:

1. A water-containing, ionically-hardenable, photocurable, ethylenically-unsaturated dental cement, comprising
 - a) finely-divided acid-reactive filler,
 - b) water-miscible acidic polymer,
 - c) photoinitiator,
 - d) water-soluble reducing agent, and
 - e) water-soluble oxidizing agent.
2. A cement according to claim 1, wherein the filler comprises metal oxide, metal salt or glass.
3. A cement according to claim 2, wherein the glass comprises fluoroaluminosilicate glass.
4. A cement according to claim 1, wherein the polymer comprises a homopolymer or copolymer of an alkenoic acid.
5. A cement according to claim 4, wherein the polymer comprises a copolymer of acrylic acid containing one or more ethylenically-unsaturated groups.
6. A cement according to claim 1, containing as a further component an ethylenically-unsaturated monomer.
7. A cement according to claim 1, wherein the reducing agent and the oxidizing agent are capable of initiating gelation of a 10:10:1 weight basis water:acrylamide:methylene bis-acrylamide mixture.

8. A cement according to claim 1, wherein the reducing agent is selected from the group consisting of ascorbic acid, cobalt (II) chloride, ferrous chloride, ferrous sulfate, hydrazine, oxalic acid, thiourea, and salts of a dithionite or sulfite anion.

9. A cement according to claim 1, wherein the reducing agent comprises ascorbic acid or thiourea.

10

10. A cement according to claim 1, wherein the oxidizing agent is selected from the group consisting of cobalt (III) chloride, tert-butyl hydroperoxide, ferric chloride, perboric acid and its salts, and salts of a permanganate or persulfate anion.

15

11. A cement according to claim 1, wherein the oxidizing agent comprises potassium or ammonium persulfate.

20

the cement has two parts respectively containing glass and polymer, and one agent is packaged with the glass and the other agent is packaged with the polymer.

25

13. A cement according to claim 1, wherein at least one of the agents is microencapsulated.

14. A cement according to claim 13, wherein the cement has two parts respectively containing glass and polymer, and both agents are packaged with the glass.

30

15. A cement according to claim 13, wherein the cement has two parts respectively containing glass and polymer, and both agents are packaged with the polymer.

35

-35-

16. A cement according to claim 13, wherein at least one of the agents is microencapsulated with water-soluble encapsulant.

5 17. A cement according to claim 13, wherein at least one of the agents is microencapsulated with water-insoluble encapsulant.

10 18. A cement according to claim 17, wherein the encapsulant comprises cellulose acetate butyrate.


15 19. A cement according to claim 1, wherein the cement contains about 3% to about 25% water, about 25% to about 85% filler, about 10% to about 50% polymer, about 0.1% to about 5% photoinitiator, about 0.02% to about 5% reducing agent, and about 0.02% to about 5% oxidizing agent.

20 20. A cement according to claim 19, wherein the cement contains about 5% to about 20% water, about 50% to about 75% filler and about 10% to about 30% polymer.

25 21. A dental cement powder, comprising finely-divided acid-reactive filler, water-soluble reducing agent and water-soluble oxidizing agent, at least one of the agents being microencapsulated.

30 22. A dental cement liquid, comprising water-miscible acidic polymer, water-soluble reducing agent and water-soluble oxidizing agent, at least one of the agents being microencapsulated.

35 23. A liquid according to claim 22, further comprising an ethylenically-unsaturated moiety.

I. CLASSIFICATION F SUBJECT MATTER (if several classification symbols apply, indicate all)		
According to International Patent Classification (IPC) or to both National Classification and IPC Int.C1. 5 A61K6/083; C04B28/28		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.C1. 5	A61K ; C04B	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT ⁹		
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
Y	WO,A,8 805 651 (DENTAL COMPOSITE LTD) 11 August 1988 see page 3, line 13 - line 39; claims ---	1-12, 19-20,23
Y	GB,A,2 189 793 (G-C SHIKA KOGYO K.K.) 4 November 1987 see page 1, line 57 - page 2, line 12; claims ---	1-12, 19-20,23
A	EP,A,0 156 564 (MINNESOTA MINING AND MANUFACTURING COMPANY) 2 October 1985 see page 3, line 13 - line 39; claims ---	13-18, 21-22
A	EP,A,0 219 058 (ERNST MÜHLBAUER KG) 22 April 1987 see column 18, line 20 - line 39; claims & US,A,4 872 936 cited in the application --- -/-	1-23
¹⁰ Special categories of cited documents: ¹⁰ "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "A" document member of the same patent family		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
30 SEPTEMBER 1992	29. 10. 92	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	G.COUSINS-VAN STEEN 	

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category *	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claims No.
A	EP,A,0 323 120 (MINNESOTA MINING AND MANUFACTURING COMPANY) 5 July 1989 cited in the application ----	
A	GB,A,2 228 001 (G-C DENTAL INDUSTRIAL CORP.) 15 August 1990 & AU-D-46717/89 cited in the application -----	

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO. US 9204164
SA 61672**

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 30/09/92

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-8805651	11-08-88	EP-A- 0312525	26-04-89
GB-A-2189793	04-11-87	JP-A- 62246514	27-10-87
		BE-A- 1000969	30-05-89
		CH-A- 670564	30-06-89
		DE-A, C 3709881	29-10-87
		FR-A- 2597334	23-10-87
		US-A- 4820744	11-04-89
		US-A- 5043361	27-08-91
EP-A-0156564	02-10-85	US-A- 4503161	05-03-85
		AU-B- 578663	03-11-88
		AU-A- 3926685	26-09-85
		CA-A- 1231700	19-01-88
		JP-A- 60223805	08-11-85
EP-A-0219058	22-04-87	DE-A- 3536076	09-04-87
		JP-A- 62149715	03-07-87
		US-A- 4872936	10-10-89
EP-A-0323120	05-07-89	AU-A- 2709388	06-07-89
		JP-A- 2006258	10-01-90
		US-A- 5100000	
GB-A-2228001	15-08-90	JP-A- 2164807	25-06-90
		AU-B- 627252	20-08-92
		AU-A- 4671789	21-06-90
		BE-A- 1002916	06-08-91
		CH-A- 680340	14-08-92
		DE-A- 3941629	21-06-90
		FR-A- 2640503	22-06-90
		NL-A- 8903089	16-07-90
		SE-A- 8904240	17-06-90
		US-A- 5063257	05-11-91